

AD-A186 005

LOCATION PLACARD (DA FORM 3779) FOR OUTSIDE STORAGE
LOCATIONS(U) ARMY MATERIEL COMMAND ALEXANDRIA VA
S A DOUGHERTY ET AL. 30 JUN 87 AMC-4-87


1/1

UNCLASSIFIED

F/G 14/5

NL





RESOLUTION TEST CHART
 NATIONAL BUREAU OF STANDARDS-1963-A

PROJECT REPORT

AMC 4-87

JUNE 1987

DTIC
ELECTE
S **D**
OCT 13 1987
D

DTIC FILE COPY **2**


AD-A186 005

LOCATION PLACARD (DA FORM 3779)
FOR
OUTSIDE STORAGE LOCATIONS

PREPARED BY:

DISTRIBUTION STATEMENT A

**Approved for public release;
Distribution Unlimited**



**US ARMY
MATERIEL COMMAND**

7177

**PACKAGING, STORAGE, AND
CONTAINERIZATION CENTER**

TOBYHANNA, PENNSYLVANIA 18466-5097

THE CONTENTS OF THIS REPORT HAVE **85**
REVIEWED AND APPROVED BY HQAMC

AD-A186005

REPORT DOCUMENTATION PAGE

Form Approved
OMB No 0704-0188
Exp Date Jun 30, 1986

1a. REPORT SECURITY CLASSIFICATION Unclassified			1b. RESTRICTIVE MARKINGS		
2a. SECURITY CLASSIFICATION AUTHORITY			3. DISTRIBUTION/AVAILABILITY OF REPORT Unclassified/Unlimited		
2b. DECLASSIFICATION/DOWNGRADING SCHEDULE					
4. PERFORMING ORGANIZATION REPORT NUMBER(S) AMC 4-87			5. MONITORING ORGANIZATION REPORT NUMBER(S) AMC 4-87		
6a. NAME OF PERFORMING ORGANIZATION AMC Packaging, Storage, and Containerization Center		6b. OFFICE SYMBOL (If applicable) SDSTO-TP-S	7a. NAME OF MONITORING ORGANIZATION U.S. Army Materiel Command		
6c. ADDRESS (City, State, and ZIP Code) Director AMCPSCC ATTN: SDSTO-TP-S Hoboken, PA 18466-5097			7b. ADDRESS (City, State, and ZIP Code) Commander, U.S. Army Materiel Command ATTN: AMCSM-POT 5001 Eisenhower Avenue Alexandria, VA 22333-0001		
8a. NAME OF FUNDING/SPONSORING ORGANIZATION		8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER		
8c. ADDRESS (City, State, and ZIP Code)			10. SOURCE OF FUNDING NUMBERS		
			PROGRAM ELEMENT NO.	PROJECT NO.	TASK NO.
					WORK UNIT ACCESSION NO.
11. TITLE (Include Security Classification) Location Placard (DA Form 3779) for Outside Storage Locations (Unclassified)					
12. PERSONAL AUTHOR(S) Dougherty, Stuart A. Strazzeri, Carmen J.					
13a. TYPE OF REPORT One time-Final		13b. TIME COVERED FROM Oct 86 to Jun 87		14. DATE OF REPORT (Year, Month, Day) 87-06-30	
15. PAGE COUNT 10					
16. SUPPLEMENTARY NOTATION					
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB-GROUP	Location Placard (DA Form 3779)		
19. ABSTRACT (Continue on reverse if necessary and identify by block number) For this project, the U.S. Army Materiel Command Packaging, Storage, and Containerization Center performed accelerated weatherometer testing on reusable plastic placards, one-time use plastic placards, protective placard holders for use with paper placards, and markers for plastic placards. The purpose was to determine techniques available to improve the durability of location placards now being used for outside storage with the Army.					
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT <input type="checkbox"/> UNCLASSIFIED/UNLIMITED <input checked="" type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION Unclassified		
22a. NAME OF RESPONSIBLE INDIVIDUAL Stuart A. Dougherty			22b. TELEPHONE (Include Area Code) (717) 894-7145		22c. OFFICE SYMBOL SDSTO-TP-S

U.S. ARMY MATERIEL COMMAND
PACKAGING, STORAGE, AND CONTAINERIZATION CENTER
Tobyhanna, PA 18466-5097

LOCATION PLACARD (DA FORM 3779) FOR OUTSIDE STORAGE LOCATIONS

AMC Project Report 4-87



Accession For	
NTIS CRA&I	<input checked="checked" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution	
Availability Codes	
Dist	Spec
A-1	

STUART A. DOUGHERTY
Distribution Facilities Specialist

CARMEN J. STRAZZERI
Packaging Specialist

June 1987

CONTENTS

	Paragraph	Page
Introduction -----	1	1
Discussion -----	2	1
Conclusions -----	3	6
Recommendations -----	4	6

1. Introduction. This project was established to determine the possibility of replacing the present DA Form 3779 with a placard of weather-resistant material for items stored outside, and to investigate techniques available to improve the durability of the location placards now being used. It is estimated that there are 40,000 outside locations in the Depot System Command.

2. Discussion. a. Background. Some depots have reported they are experiencing problems with location placards placed on items stored outside for extended periods of time. Information on the placards becomes difficult, if not impossible, to read due to the weather. These problems were verified by Center visitors to the various depots during Outreach Program visits. As a result of these visits, the Center determined that a study should be initiated to investigate alternatives to the present location placard system. Tests were performed on the following items:

- (1) Reusable plastic placards.
- (2) One-time-use plastic placards.
- (3) Protective placard holders for use with paper placards.
- (4) Markers used with plastic placards.

b. Test Method. An accelerated weathering (weatherometer) test was performed on the above items. Test specimens were exposed for a total of 300 hours in a type BH weathering apparatus (weatherometer) according to the procedures of ASTM G26, Method A (continuous exposure to light and intermittent exposure to water spray). The weathering apparatus was equipped with a water-cooled, 6500 watt, xenon arc tube with borosilicate glass inner and outer optical filters. The apparatus was operated using the conventional 2-hour program cycle of 102 minutes of light, followed by 18 minutes of light and water spray.

c. Test Results. (1) Markers. The following seven markers were evaluated in conjunction with the testing of protective placard holders and weatherable plastic placard materials:

(a) Action marker No. 55 (black). Sources: Marking Development Corporation, P.O. Box 921, Hillside, NJ 07205; Mark Tex Corporation, 161 Coolidge Avenue, Englewood, NJ 07631; Technical Products Company, RUB-CO Industrial Mall, Shoemakersville, PA 19555.

(b) Dri Mark 360 (black). Source: Dri Mark, 15 Harbor Park Drive, Port Washington, NY 11050.

(c) Dri Mark 450 (black). Source: Dri Mark, 15 Harbor Park Drive, Port Washington, NY 11050.

(d) Solid paint marker (black). Source: John P. Nissen, Jr., Company, P.O. Box 188, Glenside, PA 19038.

(e) Skilcraft wide-tip marker (black). Source: Tobyhanna Army Depot (TOAD) Self-Service Supply Store.

(f) Skilcraft felt-tip fine-point pen (black). Source: TOAD Self-Service Supply Store.

(g) PHC China marking pencil (black). Source: TOAD Self-Service Supply Store.

(2) Protective placard holders for use with paper placards. DA Forms 3779 were marked with each of the seven markers listed above and placed into plastic placard holders intended to protect the placard and markings from the adverse effects of weathering. Observations were as follows:

(a) Vinyl weatherproof envelope, chemically treated for ultraviolet light protection (Navarm Class I fold and lock document holder). Source: Navarm, 5252 Atlantic Boulevard South, P.O. Box 100, Maywood, CA 90270. This is a foldover type envelope, secured by snap fasteners. The estimated cost is \$.76 each. No discoloration or loss of flexibility of the plastic envelope was noted. The location placard remained dry. All markings were readable with minimum fading.

(b) Polyethylene (4 mil) bag (Zip Lip). Source: Franklin, Fibre-Lamitex Corporation, 903 East 13th Street, Wilmington, DE 19899. This is a zip-lock type envelope. The estimated cost is \$.05 each. No discoloration or loss of flexibility of the plastic envelope was noted. The location placard faded, but remained dry. All markings, except those of the Skilcraft fine-point pen, were readable.

(c) Plastic envelope with pressure-sensitive adhesive coating on the back (ADM Poly Envelope #GSA-30 Blank Back Loader). Source: Technical Products Company, RUB-CO Industrial Mall, Shoemakersville, PA 19555. This is a fold-over, adhesive-sealed type envelope. The estimated cost is \$.10 each. No discoloration or loss of flexibility of the plastic envelope was noted. The location placard faded, but remained dry. All markings were readable.

(d) Clear plastic envelope, open on one side. Source: Plasticraft Products, 29643 West Eight Mile Road, Livonia, MI 48152. The estimated cost of this envelope is \$.19 each. No

discoloration or loss of flexibility of the plastic envelope was noted. The location placard was faded and water stained. Water was allowed to enter the envelope through the open side. All markings were readable, although the Skilcraft fine-point pen markings were significantly faded.

(e) Table 1 provides rankings and derived benefits from use of protective placard holders.

Table 1. Rankings and Features of Protective Placard Holders

<u>Type</u>	<u>Ranking</u>	<u>Features</u>
Vinyl weatherproof envelope (Navarm)	1	Chemically treated to prevent fading, placard remained dry. Least deterioration to envelope and placard of items tested. Its only negative factor is the cost, \$.76 ea.
Polyethylene bag (Fibre-Lamitex Corp.)	2	Placard remained dry, but faded. Little deterioration to envelope.
Envelope with pressure sensitive adhesive-coated backing (Technical Products Co.)	3	Placard remained dry, but faded. Little deterioration, but more than the vinyl weatherproof envelope or polyethylene bag.
Clear plastic envelope, open on one side (Plasticraft Products)	4	Little deterioration to envelope, but water entered through open side damaging the placard.

(3) Plastic placard, one-time use. Samples of plastic placard materials were marked with each of the seven markers listed above and subjected to accelerated weathering. These materials were intended for the fabrication of weatherable, one-time-use location placards. Observations were as follows:

(a) Plastic tag with clear, plastic overlamine (LEM Lama Tag). Sources: LEM Products, Inc., P.O. Box 190, Doylestown, PA 18901 and Technical Products Co., RUB-CO Industrial Mall, Shoemakersville, PA 19555. No discoloration or signs of degradation of the placard material were noted. All markings were unaffected.

(b) White vinyl material (0.010 mil), matte finish. Source: Brandywine Fibre Products Co., 15th and Poplar Sts., Wilmington, DE 19801. The placard material exhibited

a slight yellowing with no other signs of degradation. The Skilcraft fine-point pen markings were completely faded. All other markings were readable.

(c) White plastic material, matte finish. Source: Plastic Manufacturers, Inc., 3510-30 Scotts Lane, Box 5677, Philadelphia, PA 19129-0677. No discoloration of the placard material was noted, but signs of degradation (surface embrittlement) were evident. The Skilcraft fine-point pen markings were completely faded. All other markings were readable.

(d) White, opaque, high-impact polystyrene, matte finish. Source: Commercial Plastics and Supply Corp., 342 Fourth St., Trenton, NJ 08638. The placard material exhibited a light yellow discoloration and signs of degradation (surface embrittlement). The Skilcraft fine-point pen markings were completely faded. All other markings were readable, although those of the Skilcraft wide-tip marker were slightly faded.

(4) Plastic placards, reusable. Samples of plastic placard materials were marked with each of the seven markers listed above, and subjected to accelerated weathering. These materials were intended for the fabrication of weatherable, reusable location placards. Observations were as follows:

(a) Blue plastic material, gloss finish. Source: Plastic Manufacturers, Inc., 3510-30 Scotts Lane, Box 5677, Philadelphia, PA 19129-0677. The placard material exhibited a light yellowing which changed the color of the material to a greenish-blue. No other signs of degradation were noted. The Skilcraft fine-point pen markings were completely faded. All other markings were readable, although those of the Skilcraft wide-tip marker were very faded. None of the remaining markings, including those of the PHC China marking pencil, could be removed mechanically by rubbing with a dry gauze pad.

(b) Yellow polished rigid vinyl, gloss finish. Source: Commercial Plastics and Supply Corp., 342 Fourth St., Trenton, NJ 08638. The placard material exhibited fading, but no other signs of degradation. The Skilcraft fine-point pen markings were completely faded. All other markings were readable, although those of the Skilcraft wide-tip marker were slightly faded. None of the remaining markings, including those of the PHC China marking pencil, could be removed mechanically by rubbing with a dry gauze pad.

(c) White polished vinyl (0.010 mil), gloss finish. Source: Brandywine Fibre Products Co., 15th and Poplar Sts., Wilmington, DE 19801. The placard material exhibited a slight yellowing with no other signs of degradation. The Skilcraft

fine-point pen markings were completely faded. All other markings were readable. None of the remaining markings, including those of the PHC China marking pencil, could be removed mechanically by rubbing with a dry gauze pad.

(d) Vinyl weatherproof envelope, chemically treated for ultraviolet light protection of the envelope (Navarm Class I fold and lock document holder). Source: Navarm, 5252 Atlantic Blvd. South, P.O. Box 100, Maywood, CA 90270. The test specimen consisted of a DA Form 3779 placed inside the weatherproof envelope. The markings were applied to the exterior of the envelope using the PHC China marking pencil. These markings could not be completely removed mechanically by rubbing with a dry gauze pad.

(5) Cleanability of reusable plastic placards using solvents. Following accelerated weathering, a test was conducted to determine the cleanability of the reusable plastic placards, using four common solvents: methyl alcohol, acetone, methyl ethyl ketone (MEK), and 1,1,1-trichloroethane. An attempt was made to remove the markings from the placard material by rubbing with a gauze pad saturated with one of these solvents. Results of this test were as follows:

(a) Blue plastic material, gloss finish (Plastic Manufacturers, Inc.). The methyl alcohol removed all of the markings without damaging the placard material. The acetone and MEK removed all of the markings, but also attacked the placard material, dulling its surface finish. The trichloroethane removed only the markings of the Nissen solid paint marker and the PHC China marking pencil.

(b) Yellow polished rigid vinyl, gloss finish (Commercial Plastics and Supply Corp.). The methyl alcohol removed only the markings of the Nissen solid paint marker, the Dri Mark 360 marker, and the Dri Mark 450 marker. The acetone and MEK removed all of the markings, but also attacked the placard material. The trichloroethane removed only the markings of the PHC China marking pencil.

(c) White polished vinyl (0.010 mil), gloss finish (Brandywine Fibre Products Co.). The methyl alcohol removed all of the markings without damaging the placard material. The acetone and MEK removed all of the markings, but also attacked the placard material. The trichloroethane removed only the markings of the Nissen solid paint marker and the PHC China marking pencil.

(d) Vinyl weatherproof envelope, chemically treated for ultraviolet light protection of the envelope (Navarm Class I fold and lock document holder). Only the PHC China marking pencil was used to apply markings to the exterior surface of

the envelope. The methyl alcohol did not remove the markings. The acetone and MEK removed the markings, but also attacked the plastic envelope. The trichloroethane removed the markings without damaging the plastic envelope.

3. Conclusions. a. All tested markers, with the exception of the Skilcraft felt-tip, fine-point writing pen, were readable on the reusable and non-reusable plastic placard materials following accelerated weathering.

b. The use of sealing-type plastic placard holders provides a feasible method of protecting the current DA Form 3779 from the effects of weathering in outside storage locations.

c. Plastic placard materials are susceptible to embrittlement and progressive deterioration when exposed to sunlight and other outdoor weathering conditions, unless treated with an ultraviolet light inhibitor.

d. To be reusable, plastic placards must have a gloss finish to facilitate removal of prior markings.

e. Plastic placards designed for one-time use require a clear, plastic overlamine to protect the markings and the plastic placard material from degradation due to long-term exposure to outdoor weathering conditions.

f. Markings should be removed from reusable plastic placards with either methyl alcohol or trichloroethane depending on the type of marking.

g. Neither acetone nor MEK should be used to remove prior markings from a reusable plastic placard since these solvents will attack and damage the plastic placard material.

h. After exposure to sunlight and weathering conditions, previous markings cannot be readily removed from the reusable plastic placards without the aid of an organic solvent.

i. Reusable plastic placard materials have shown signs of embrittlement during testing, indicating limited use under long-term exposure to sunlight and outdoor weathering conditions.

4. Recommendations. a. That reusable plastic placards not be used in outside storage locations.

b. That the current DA Form 3779 be enclosed in protective plastic placard holders for protection from the effects of weathering.

c. That the protective holders be chemically treated for ultraviolet light resistance.

END
DATE
FILMED
JAN
1988